

SHANGRAO RUICHEN SEALING CO., LTD DONGGUAN RUICHEN SEALING CO., LTD

Address: Road 8.Yanshan Industrial Estate, Shangrao City, 334500, Jiangxi Prov., CHINA Tel: +86-18024335478 E-mail: aaron@dgork.com

MATERIALS	S TEST REPORT					
EPDM45 BLACK N	E4501N) COMPOUND					
ASTM D2000 M3CA 457 A25 B35 C32 EA14 F17						
Press Cure		Post Cure Sheet : 1 hrs 125°C				
Sheet : 7min 170 $^\circ \!$	S					
Button : 10 min 170 °C	Button : 1 hrs 125°C					
ORIGINAL PROPERTIES	SPECIFICATION	TEST RESULT	ASTM TEST METHOD			
HARDNESS SHORE A	45°±5	48	D2240			
TENSILE STRENGTH, MPA, MIN	≥7	7.25	D412			
ULTIMATE ELONGATION, %, MIN	≥350	507.62	D412			
SPECIFIC GRAVITY (g/cm ³)		1.15	D297			
HEAT RESISTANCE 70 H . AT 125 ℃ (A25)			D865			
CHANGE IN HARDNESS, POINTS	+10	+10				
CHANGE IN TENSILES STRENGTH, %	-20	+0.96				
CHANGE IN ULTIMATE ELONGATION,MAX %	-40	-36.75				
COMPRESSION SET, MAX, 22H AT 125 $^\circ C$ (B35)	≤70	61.11	D395			
RESISTANCE TO OZONE , TEST METHOD D 1171, (C32)						
EXPOSURE METHOD B		PASS	D1171			
WATER RESISTANCE:100 $^\circ\!\!\!C$,70H (EA14)						
VOLUME CHAGE,%	±5	+3.5	D471			
LOW-TEMPERATURE BRITTLENESS NONBRITTLE						
AFTER 3MIN AT -40°C (F17)	NONBRITTLE	PASS	D2137			

Remark:

1. The data are based on testing slabs I buttons and are for reference purpose only.

2. Our compound can meet above -mentioned ASTM 2000 Spec.

3. This information is, to the best of our knowledge, accurate reliable to the date indicated.

4. The above mentioned data have been obtained by tests we consider as reliable, We don't assure that

- the same results can be obtained other laboratories, using different conditions by the preparation and -evaluation of the samples.

Approved By:	Checked By:	Yunli Tu	Tested By:	Jianjun Zhu
--------------	-------------	----------	------------	-------------

ORK-FM-095A-1