

## SHANGRAO RUICHEN SEALING CO.,LTD DONGGUAN RUICHEN SEALING CO.,LTD

Address: Road 8.Yanshan Industrial Estate, Shangrao City, 334500, Jiangxi Prov., CHINA Tel: +86-18024335478 E-mail: aaron@dgork.com

MATERIALS TEST REPORT EPDM80 BLACK WRC(E8001WRC) COMPOUND ASTM D2000 M3DA 810 A26 B36 C32 EA14 F19							
				Press Cure Sheet : 7min 170℃ Button : 10 min 170℃	Post Cure Post Cure Button : 1 hrs 150°C		
HARDNESS SHORE A	80°±5	80	D2240				
TENSILE STRENGTH, MPA, MIN	≥10	13.00	D412				
ULTIMATE ELONGATION, %, MIN	≥150	257.28	D412				
SPECIFIC GRAVITY (g/cm <sup>3</sup> )		1.20	D297				
HEAT RESISTANCE 70 H . AT 150°C (A26)			D865				
CHANGE IN HARDNESS, POINTS	+10	+6					
CHANGE IN TENSILES STRENGTH, %	-20	-16.00					
CHANGE IN ULTIMATE ELONGATION,MAX %	-20	-14.95					
COMPRESSION SET, MAX, 22H AT150 °C (B36 )	≤25	19.80	D395				
RESISTANCE TO OZONE , TEST METHOD D 1171,(C32)			D1171				
EXPOSURE METHOD B		PASS					
WATER RESISTANCE:100 $^\circ\!\mathrm{C}$ ,70H (EA14)							
VOLUME CHAGE,%	€-5~+5 )	+3.6	D471				
LOW-TEMPERATURE BRITTLENESS NONBRITTLE							
AFTER 3MIN AT -55°C (F19)	NONBRITTLE	PASS	D2137				

Remark:

1. The data are based on testing slabs I buttons and are for reference purpose only.

2. Our compound can meet above -mentioned ASTM 2000 Spec.

3. This information is, to the best of our knowledge, accurate reliable to the date indicated.

4. The above mentioned data have been obtained by tests we consider as reliable, We don't assure that
- the same results can be obtained other laboratories, using different conditions by the preparation and
-evaluation of the samples.

 Approved By:
 Checked By:
 Yunli Tu
 Tested By:
 Jianjun Zhu

ORK-FM-095A-1