

SHANGRAO RUICHEN SEALING CO.,LTD DONGGUAN RUICHEN SEALING CO.,LTD

Address: Road 8. Yanshan Industrial Estate, Shangrao City, 334500, Jiangxi Prov., CHINA

Tel: +86-18024335478 E-mail: aaron@dgork.com

MATERIALS TEST REPORT

FKM70 WHITE (V7009) COMPOUND

ASTM D2000 M2HK 710 A1-10 B38 E078 EF31 F13

Press Cure	Post Cure Sheet: 16 hrs230°C Button: 16 hrs 230°C			
Sheet : 10min 170 $^{\circ}\!$				
Button : 10 min 170 $^{\circ}\mathrm{C}$				
ORIGINAL PROPERTIES	SPECIFICATION	TEST RESULT	ASTM TEST METHOD	
HARDNESS SHORE A	70°±5	71	D2240	
TENSILE STRENGTH, MPA, MIN	≥10	10.43	D412	
ULTIMATE ELONGATION, %, MIN	≥175	250.17	D412	
SPECIFIC GRAVITY (g/cm³)		1.85	D297	
HEAT RESISTANCE 70 H . AT 250 °C (A1-10)			D573	
CHANGE IN HARDNESS, POINTS	+10	+2		
CHANGE IN TENSILES STRENGTH, %	-25	+20.90		
CHANGE IN ULTIMATE ELONGATION,MAX %	-25	-15.72		
COMPRESSION SET, MAX, 22H AT 200℃ (B38)	≤30	16.23	D395	
FLUID RESISTANCE FUEL.101. 70H AT 200℃ (EO78)			D471	
CHANGE IN HARDNESS, POINTS	-15~+5	-8		
CHANGE IN TENSILES STRENGTH, MAX %	-40	-22.3		
CHANGE IN ULTIMATE ELONGATION,MAX %	-20	-10.59		
CHANGE IN VOLUME %	0~+15	+6.87		
FLUID RESISTANCE FUEL C, 70H AT 23℃ (EF31)			D471	
CHANGE IN HARDNESS, POINTS	±5	-3		
CHANGE IN TENSILES STRENGTH, MAX %	-25	-12.6		
CHANGE IN ULTIMATE ELONGATION,MAX %	-20	13.8		
CHANGE IN VOLUME %	0~+10	+3.9		
LOW-TEMPERATURE BRITTLENESS NONBRITTLE				
AFTER 3MIN AT -10°C (F13)	NONBRITTLE	PASS	D2137	

Remark:

- 1. The data are based on testing slabs I buttons and are for reference purpose only..
- 2. Our compound can meet above -mentioned ASTM 2000 Spec.
- 3. This information is, to the best of our knowledge, accurate reliable to the date indicated.
- 4. The above mentioned data have been obtained by tests we consider as reliable, We don't assure that
- the same results can be obtained other laboratories, using different conditions by the preparation and -evaluation of the samples.

	Approved By	Frankie Fang	Checked By:	Yunli Tu	Tested By:	Jianjun Zhu
--	-------------	--------------	-------------	----------	------------	-------------