

SHANGRAO RUICHEN SEALING CO.,LTD DONGGUAN RUICHEN SEALING CO.,LTD

Address: Road 8.Yanshan Industrial Estate Shangrao City, 334500, Jiangxi Prov.CHINA

Tel: +86-18024335478 E-mail: aaron@dgork.com

MATERIALS TEST REPORT

NBR45 BLACK FDA (N4501F) COMPOUND

ASTM D2000 M2BG 457 A14 B14 EO14 EO34 EA14 F17

Press Cure	Post Cure		
Sheet : 5min 170°C	Sheet: 1 hrs 120°C Button: 1 hrs 120°C		
Button : 10 min 170℃			
ORIGINAL PROPERTIES	SPECIFICATION	TEST RESULT	ASTM TEST METHOD
HARDNESS SHORE A	45°±5	47	D2240
TENSILE STRENGTH, MPA, MIN	≥7	7.71	D412
ULTIMATE ELONGATION, %, MIN	≥400	540.97	D412
SPECIFIC GRAVITY (g/cm³)		1.19	D297
HEAT RESISTANCE 70 H . AT 100 ℃ (A14)			D573
CHANGE IN HARDNESS, POINTS	+/-15	+10	
CHANGE IN TENSILES STRENGTH, %	+/-30	-21.53	
CHANGE IN ULTIMATE ELONGATION,MAX %	-50	-37.38	
COMPRESSION SET, MAX, 22H AT 100°C(B14)	≤25	23.03	D395
FLUID RESISTANCE NO.1 OIL, 70H AT 100 $^{\circ}$ (EO14)			D471
CHANGE IN HARDNESS, POINTS	-5~+10	+10	
CHANGE IN TENSILES STRENGTH, MAX %	-25	-2.08	
CHANGE IN ULTIMATE ELONGATION,MAX %	-45	-41.8	
CHANGE IN VOLUME %	-10~+5	-9.43	
FLUID RESISTANCE NO.3 OIL, 70H AT 100℃ (EO34)			D471
CHANGE IN HARDNESS, POINTS	-10~+5	+5	
CHANGE IN TENSILES STRENGTH, MAX %	-45	-15.56	
CHANGE IN ULTIMATE ELONGATION,MAX %	-45	-39.31	
CHANGE IN VOLUME %	0~+25	0.47	
WATER RESISTANCE:100℃,70H (EA14)			D471
CHANGE IN HARDNESS, POINTS	±10	+2	
CHANGE IN VOLUME %	±15	-2.38	
LOW-TEMPERATURE BRITTLENESS NONBRITTLE			
AFTER 3MIN AT -40°C (F17)	NONBRITTLE	PASS	D2137

Remark:

- 1. The data are based on testing slabs I buttons and are for reference purpose only..
- 2. Our compound can meet above -mentioned ASTM 2000 Spec.
- 3. This information is, to the best of our knowledge, accurate reliable to the date indicated.
- 4. The above mentioned data have been obtained by tests we consider as reliable, We don't assure that
 - the same results can be obtained other laboratories, using different conditions by the preparation and -evaluation of the samples.

Approved By: Audit By:	Yunli Tu	Test By:	Jianjun Zhu
------------------------	----------	----------	-------------